

Table 3.- Cyanide Solubility Results, Full House Project

Composite I.D.	Au		Solubility, %	Ag	
	Assay oz/ton ore	CN Sol		CN Sol oz/ton ore	
FH-CMP-1	0.165	0.146	88.5 ¹⁾	0.014	

1) Based on average head grade